

化学品名		聚四氟乙烯	聚丙烯	聚醚砜	尼龙	混合纤维素	聚偏氟乙烯
CHEMICAL		PTFE	PP	PES	NYLON	MCE	PVDF
苯甲醇 100%	Benzyl alcohol 100%	R	R	R	R	NR	R
丁醇	Butanol	R	R	R	R	R	R
乙醇	Ethanol	R	R	R	R	GR	R
甲醇	Methanol	R	R	R	LR	NR	R
乙醚	Ethy ether	R	LR	R	R	--	--
四氢呋喃	Tetrahyarofuran	LR	R	NR	R	NR	NR
苯	Benzene	LR	NR	LR	LR	GR	R
甲苯	Tiluene	LR	NR	LR	NR	GR	R
二甲苯	Xylene	LR	NR	LR	LR	GR	R
甘油	Glycerol	R	R	R	R	R	R
丙二醇	Propylene Glycol	--	R	NR	R	--	--
四氯化碳	Carbon Teteachloride	LR	LR	LR	LR	R	R
二氯甲烷	Methylene Chloride	LR	LR	NR	LR	NR	NR
三氯乙烯	Trichloro Ethylene	NR	LR	LR	LR	NR	R
冰醋酸	Acetic acid glacial	R	R	R	NR	NR	R
盐酸 6N	Hydrochloric acid 6N	R	R	--	NR	NR	TST
硝酸 6N	Nitric acid 6N	R	R	--	NR	NR	R
硫酸(浓)	Sulfuric acid (conc)	R	R	NR	NR	--	--
氢氧化钾 3N	Potassium hydroxide 3N	R	R	R	R	NR	R
氢氧化钠 3N	Sodium hydroxide 3N	R	R	R	R	NR	R
氢氧化钠 6N	Sodium hydroxide 6N	R	R	R	R	--	--
润滑油	Lubricating oil	R	R	NR	R	R	--
花生油	Peanut oil	R	R	--	R	R	--
芝麻油	Sesame oil	R	R	NR	R	R	--
丙酮	Acetone	R	R	NR	R	NR	NR
环己酮	Cyclo hexanone	R	R	NR	--	NR	NR
二甲基甲酰胺	Dimethyl From amide	R	R	NR	R	NR	NR
甲醛 4%	Formal dehyde 4%	R	R	R	R	--	--
汽油	Gasoloine	LR	LR	R	LR	R	R
苯酚	Phenol liquified	R	R	NR	R	R	R
吡啶	Pyridend	R	LR	NR	LR	NR	NR
水	Water	R	R	R	R	--	--
乙腈	Acctonitrile	R	LR	R	LR	NR	NR
异丙醇	Isopropanol	R	R	R	R	NR	R

注：R=推荐；LR=有限推荐；NR=不推荐；GR=一般推荐；TST=推荐用户预先测试；--：未测试

Note：R=Recommended; LR=Limited Recommendation; NR=Not Recommended; GR=Generally Recommended; TST =Testing Recommended; --: Not tested

* 本表是依据化学公开出版物的兼容性表编辑所得，仅供分析者参考，不代表本公司最终数据。

* This table is made according to the compatibility table of chemistry publications. It is for reference only and not represents the final data of our company.